

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 148 072 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
24.10.2001 Bulletin 2001/43

(51) Int Cl.7: **C08F 216/14, C08F 214/00**

(21) Application number: **01108598.2**

(22) Date of filing: **05.04.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Navarrini, Walter**
Boffalora Ticino, Milano (IT)

(30) Priority: **21.04.2000 IT MI000901**

(74) Representative: **Sama, Daniele, Dr. et al**
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(54) **Fluoroelastomers**

(57) Fluoroelastomers comprising in the polymer chain units deriving from fluorovinylethers having the formula:



wherein R is a C₂-C₆ linear, branched or C₅-C₆ cyclic (per) fluoroalkyl group, or a C₂-C₆ linear, branched (per) fluoro oxyalkyl group containing from one to three oxygen atoms; when R is fluoroalkyl or fluoroxyalkyl group as above defined, it can contain from 1 to 2 atoms, equal or different, selected from the following: H, Cl, Br, I; X = F, H.

EP 1 148 072 A2

Descripti n

[0001] The present invention relates to fluorovinylethers, the process for preparing them and the polymers obtainable therefrom.

[0002] It is well known that perfluoroalkylvinylethers are used as monomers for the olefin copolymerization, specifically tetrafluoroethylene, vinylidene fluoride, chlorotrifluoroethylene (CTFE), hexafluoropropene. The introduction of small amounts of perfluoroalkylvinylethers in elastomeric polymers implies a higher polymer processability and better hot mechanical properties. The introduction of high amounts of perfluorovinylethers in crosslinkable fluoropolymers implies elastomeric properties at low temperature of fluorinated rubbers.


[0003] The need was felt, in the field of fluorinated polymer materials, to produce elastomers having improved properties at low temperatures. Such properties can generally be expressed by the glass transition temperature T_g.

[0004] A lower T_g allows to have polymers which can be used at lower temperatures and therefore to have available elastomers with a wider use range. To obtain the combination of the above mentioned properties, fluorovinylethers must have a high unitary capability to modify the backbone properties, as well as high reactivity to be used as comonomers in elastomeric fluoropolymers. It was desirable to have available vinylethers obtainable by simple processes having a limited number of steps. Preferably it would be desirable to have available a continuous process for preparing said vinylethers.

[0005] To solve the above technical problem, fluorovinylethers having different structural properties, have been proposed in the prior art. However from the prior art, hereinafter described, various unsolved problems exist in the perfluorovinylether synthesis and in the preparation of the corresponding polymers having the combination of the above mentioned properties.

[0006] USP 3,132,123 describes the preparation of perfluoroalkylvinylethers, of the corresponding homopolymers and copolymers with TFE. Homopolymers are obtained under extreme experimental conditions, by using polymerization pressures from 4,000 to 18,000 atm. The perfluoromethylvinylether (PMVE) homopolymer is an elastomer: the T_g is not reported.

The general formula of the described vinylethers is the following:



wherein R⁰_F is a perfluoroalkyl radical preferably from 1 to 5 carbon atoms. A process for preparing these vinylethers is described in USP 3,291,843 wherein the starting acylfluoride is salfied and pyrolyzed with carbonates also in the presence of solvents. By this process undesired hydrogenated byproducts are obtained.


[0007] USP 3,450,684 relates to vinylethers having the formula:



wherein X⁰ = F, Cl, CF₃, H and n' can range from 1 to 20. Also homopolymers obtained by UV polymerization are reported. The exemplified copolymers are not characterized by their mechanical and elastomeric properties at low temperatures.

[0008] USP 3,635,926 relates to the emulsion copolymerization of perfluorovinylethers with TFE, showing that the presence of -COF acylfluoride end groups makes the polymers unstable. The same phenomenon was already reported in USP 3,085,083 in the perfluorovinylether polymerization systems in solvent.

[0009] USP 3,817,960 relates to the preparation and polymerization of perfluorovinylethers having the formula



wherein n" can range from 1 to 5. The compound synthesis is complex, it requires three steps. The preparation of the starting compound CF₃O(CF₂O)_nCF₂C(O)F is carried out by oxidation at low temperature in the presence of U.V. radiations; besides the condensation with HFPO (hexafluoropropenoxide) and the subsequent alkaline pyrolysis is necessary. No characterization data on the above indicated properties are reported. With regard to this see patent application DE 19,713,806.


[0010] USP 3,896,179 relates to the separation of "primary" isomers of perfluorovinylether, for example of CF₃CF₂CF₂OCF=CF₂ from the corresponding less stable "secondary" isomers CF₃(CF₃)CFOCF=CF₂. The latter are undesired products as regards both the polymer preparation and the poor properties of the obtained polymers.

[0011] USP 4,340,750 relates to the preparation of perfluorovinylethers having the formula



wherein R^0 is a C_1 - C_{20} perfluoroalkyl optionally containing oxygen, $\text{X}^1=\text{H}$, Cl , Br , F , COOR^0 , $\text{CONR}^0\text{R}'$ wherein R^0 is a C_1 - C_{10} alkyl group and R' represents H or a C_1 - C_{10} alkyl group. In the preparation of these compounds an acylfluoride together with iodine and tetrafluoroethylene is used, avoiding the final step of the acylfluoride pyrolysis which comes from the perfluoro-propene epoxide, by a deiodofluorination reaction, which takes place with low yields.


[0012] USP 4,487,903 relates to the preparation of fluoroelastomeric copolymers using perfluorovinylethers having the formula:



wherein n° ranges from 1 to 4; $\text{Y}^0=\text{F}$, Cl , CF_3 , H ; X^2 can be C_1 - C_3 perfluoroalkyl group, C_1 - C_3 ω -hydroperfluoroalkyl group, C_1 - C_3 ω -chloroperfluoroalkyl group. The polymer has a content of fluorovinylether units content ranging from 15 to 50% by moles. These vinyl ethers give copolymers which at low temperatures have better properties than those of the above mentioned perfluorovinylethers PVE (perfluoropropylvinylether) and MVE type. In the patent it is disclosed that in order to have good properties at low temperature, the presence of at least two ether bonds in the side chain adjacent to the double bond is required. Furthermore from the patent it results that for n° values higher than 4 it is difficult to purify the monomers and the effect on the decrease of the polymer T_g is lower. Besides the reactivity of the described vinyl ethers is very low and it is difficult to obtain polymers having a high molecular weight able to give good elastomeric properties for the indicated applications.


A TFE/perfluorovinylether copolymer ($n^\circ=2$) 31/69 % by weight with T_g of -32°C is exemplified. However the polymer is obtained with very long reaction times (96 hours of polymerization). Also in this case no characterization data of the cured elastomer are given.

[0013] EP 130,052 describes the perfluorovinylpolyether (PVPE) polymerization which leads to amorphous perfluoropolymers with a T_g ranging from -15 to -100°C . The described polymers have T_g values reaching up to -76°C ; the further T_g decrease is obtained by using perfluoropolyethers as plasticizers. In the patent copolymers and terpolymers of TFE and MVE with vinyl ethers (PVPE) having the formula



are described, wherein n''' ranges from 3 to 30 and R^0 is a perfluoroalkyl group. Due to purification difficulties, the used vinyl ethers are vinyl ether mixtures with different n''' values. According to said patent the most evident effect on the T_g decrease is shown when n''' is equal to or higher than 3, preferably higher than 4. According to the polymerization examples described in said patent the final mass of the polymer, besides the hot and under vacuum treatment, must then be washed with freon® TF in order to remove all the unreacted monomer (PVPE). From the Examples it results that the reactivity of all the described monomers (PVPE) is poor.

[0014] USP 4,515,989 relates to the preparation of new intermediates for the fluorovinylether synthesis. According to the patent the vinyl ether synthesis is improved by using an intermediate able to more easily decarboxylate. For its preparation fluoroepoxides of formula:



wherein $\text{X}^3=\text{Cl}$, Br are used.


[0015] USP 4,766,190 relates to the polymerization of perfluorovinylpolyethers (PVPE) similar to those of USP 4,487,903 with TFE and low perfluoropropene percentages, in order to increase the mechanical properties of the obtained polymers.

[0016] EP 338,755 relates to the preparation of perfluorinated copolymers by using direct fluorination of partially fluorinated copolymers. More reactive partially fluorinated monomers are used, the obtained polymers are fluorinated with elemental fluorine. The fluorination step requires a supplementary process unit, besides in this step elemental fluorine is used, which is a highly oxidizing gas, with the consequent precautions connected to its use. Besides in the patent it is stated that in order not to compromise the fluorination reaction and the properties of the obtained polymer, using the invention process the percentage of the comonomer in the polymer cannot exceed 50% by moles.

[0017] USP 5,268,405 reports the preparation of perfluorinated rubbers having a low T_g, by using high viscosity perfluoropolyethers as plasticizers of perfluorinated rubbers (TFE/MVE copolymers). However during the use perfluoropolyether bleeds take place. This is true especially for the the PFPE having a low molecular weight (low viscosity): in said patent, therefore, the high viscosity PFPE use is suggested, and therefore the low viscosity PFPEs must previously be removed.

[0018] USP 5,350,497 relates to the preparation of perfluoroalkylvinylethers by fluorination with elemental fluorine of hydrofluorochloroethers and subsequent dechlorination.

[0019] USP 5,401,818 relates to the preparation of perfluorovinylethers of formula:



(wherein R¹_f is a C₁-C₃ perfluoroalkyl radical and m' is an integer ranging from 1 to 4) and of the corresponding copolymers having improved properties at low temperature. The preparation of said perfluorovinylethers is carried out by 7 steps, some of them have very low yields, and comprise also a fluorination with elemental F₂. The reactivity of said perfluorovinylethers is anyhow low.

[0020] As it is shown from the above reported prior art, the perfluorovinylether synthesis generally involves a multistep process with low yields (USP 3,132,123, USP 3,450,684), with additional purifications to remove undesired isomers (USP 3,896,179) and the need to control the undesired hydrogenated by-products (USP 3,291,843). Alternatively, in the synthesis substances acting as intermediates, which are suitably prepared, and which allow to eliminate said drawbacks (USP 4,340,750, USP 4,515,989), are used.

[0021] Furthermore in some cases the vinylether preparation requires the fluorination with elemental fluorine of partially fluorinated intermediates (USP 5,350,497); or, to avoid synthesis and low reactivity problems of the perfluorovinylethers, fluorination of partially fluorinated polymers (EP 338,755) is suggested.

[0022] Other problems shown in the prior art relate to the low reactivity of the perfluorovinylethers, which makes it necessary the recovery of the unreacted monomers from the reaction products (UK 1,514,700), and the stability problems for the polymers having -C(O)F end groups (USP 3,635,926). These last can be furtherly transformed by suitable reactants in order to increase the stability of the fluorinated polymer (EP 178,935).

[0023] Perfluoroalkylvinylethers are furthermore used to confer to the fluorinated rubbers good properties at low temperatures, and specifically to lower the glass transition temperature.

[0024] By increasing the perfluoroalkyl units forming the side perfluoroalkyl substituent, the T_g of the respective obtainable amorphous copolymers decreases, but at the same time the vinylether reactivity drastically decreases, making it difficult or impossible to obtain polymers having a sufficiently high molecular weight for giving to the polymers the desired elastomeric properties, and besides making more evident the problems previously shown for the recovery of the unreacted monomer from the polymerization products or from the polymer itself (USP 4,487,903 - EP 130,052). In some cases, where the monomer cannot be completely removed by simple stripping under vacuum, more washings must then be carried out with fluorinated solvents for completely eliminating the unreacted vinylether from the polymer mass.

[0025] The amorphous copolymers of TFE with perfluoromethylvinylether have a T_g around 0°C or slightly lower (Maskornik, M. et al. "ECD-006 Fluoroelastomer - A high performance engineering material". Soc. Plast Eng. Tech. Pao. (1974), 20, 675-7).

[0026] The T_g extrapolated value of the MVE homopolymer is of about -5°C (J. Macromol. Sci.-Phys., B1(4), 815-830, Dec. 1967).

[0027] In USP 5,296,617 and 5,235,074 there is described the hypofluorite CF₂(OF)₂ reactivity towards unsaturated products, which contemporaneously leads to the formation of the dioxolane derivative and to the fluorination compound of the olefin itself. In EP 683,181 there is described the CF₂(OF)₂ reactivity towards olefins which leads to the formation of linear reaction compound between one hypofluorite molecule and two molecules of the same olefin, for the preparation of symmetric dienes.

[0028] More specifically fluoroelastomers, suitable to the preparation of O-rings, based on monomeric units deriving from vinylidene fluoride (VDF), hexafluoropropene (HFP), perfluoroalkylvinylethers (PAVE) such as for example methylvinylether, and optionally tetrafluoroethylene (TFE), which are curable by ionic route, have high elastomeric properties at low and high temperatures and show good processability, e.g. increased mould release after curing (see USP 5,260,393). Said fluoroelastomers show improved properties with respect to the copolymers formed by VDF and HFP units, used in the O-ring preparation. In fact said last copolymers show good hot properties, but poor properties at low temperatures.

[0029] It is also known that fluoroelastomers having better cold properties are those based on VDF, PAVE and optionally TFE units, curable by radical route with peroxides and crosslinking agents.

[0030] By this kind of crosslinking, however, the process for producing manufactured articles is more complex with

respect to the crosslinking of ionic type.

[0031] Fluoroelastomers based on monomeric units deriving from vinylidenefluoride (VDF), which are curable by ionic route and suitable for the production of shaft seals and fuel hoses (see USP 5,260,392), are also known.

[0032] As it is known, the preparation of such manufactured articles requires elastomers having an optimal combination of the following properties: good resistance properties to motor oils and/or petrols, good resistance properties at high temperatures as well as good cold behaviour and in particular, for the manufactured articles as shaft seals, good processability in both compression and injection moulding and also good curing rate.

[0033] It is known to use for such manufactured articles fluoroelastomers formed by monomeric units of VDF, perfluoroalkylvinylethers (PAVE) and tetrafluoroethylene (TFE).

[0034] Said copolymers have good properties at low temperatures, however they show the drawback to be curable only by peroxidic route, with all the drawbacks due to said curing method, such as for example the need to carefully control the temperatures in the compounding operations, the short scorch and thermal activation times.

[0035] Fluoroelastomers having an improved processability and very good mechanical and elastic properties curable both by ionic and peroxidic route, are also known.

[0036] It is also known that an improvement in the fluoroelastomer processability is obtainable by suitably mixing polymers having a different molecular weight distribution. This inevitably implies, besides swelling phenomena after extrusion, a worsening in the mechanical properties and in the final product mouldability.

[0037] Said fluoroelastomers show an improved processability, especially during the blend calendaring, combined with very good mechanical and workability properties during the extrusion and the injection moulding, together with a very good mould release. These fluoroelastomers are obtained by introducing in the polymer chain small amounts of a bis-olefin (see USP 5,585,449).

[0038] The above described fluoroelastomers have however the drawback to show at low temperatures properties not yet able to satisfy the most urgent requirements of resistance at low temperatures, such as for example in car industry, wherein materials are required having the combination of the following properties:

- chemical resistance to petrols additived with alcohols or MBTE or other polar compounds,
- high resistance at low temperatures such as for example shown by TR 10 (ASTM D 1329 method),
- very low Tg,
- maintenance of good elastomeric properties, such as for example mechanical and sealing properties, in particular at high temperatures.

[0039] The Applicant has surprisingly and unexpectedly found that it is possible to solve the above technical problem as described hereinafter, by using special fluorovinylethers, which are furthermore easily synthesizable and obtainable by a continuous process.

[0040] An object of the present invention are fluoroelastomers comprising in the polymer chain units deriving from fluorovinylethers of general formula:



wherein R is a C₂-C₆ linear, branched or C₅-C₆ cyclic (per)fluoroalkyl group, or a C₂-C₆ linear, branched (per)fluoroalkoxy group containing from one to three oxygen atoms; when R is a fluoroalkyl or fluoroalkoxy group as above defined it can contain from 1 to 2 atoms, equal to or different from each other, selected from the following: H, Cl, Br, I;



[0041] The fluorovinylethers of general formula:



wherein Y = F, OCF₃; X as above defined, are preferred among the compounds of formula (I).

[0042] The perfluorovinylethers of formula:



wherein Y is as above defined, are furtherly preferred.

[0043] The perfluorovinylether having the formula:




is still furtherly preferred.

[0044] Surprisingly, the vinyl ethers according to the invention show the advantages reported hereinafter with respect to the known vinyl ethers.


[0045] The obtainable advantages can be attributed to the $-\text{OCF}_2\text{O}-$ unit directly bound to the ethylene unsaturation.

[0046] The Tg lowering obtained with the vinyl ethers of the invention is connected to the presence of the $(-\text{OCF}_2\text{O}-)$ unit directly bound to the unsaturation. The Tg lowering is surprisingly so evident to be defined a primary effect.


[0047] In fact if the vinyl ether of the invention with two oxygen atoms is used:




the Tg lowering, in copolymers with TFE having vinyl ether percentages of about 46% by weight is of 35°C with respect to PVE



and of 15°C with respect to the vinyl ether having the same formula, but with the second oxygen atom in a different position and without showing the characteristic unit $(-\text{OCF}_2\text{O}-)$



[0048] It is still more surprising to notice that with respect to MVE



the β -PDE vinyl ether does not give any advantage as regards Tg.

[0049] On the contrary the primary effect of the $(-\text{OCF}_2\text{O}-)$ unit results very clear with the vinyl ethers of the invention (MOVE).

[0050] It has been found that the $(-\text{OCF}_2\text{O}-)$ unit bound to the ethylene unsaturation of the vinyl ethers of the invention increases the vinyl ether reactivity, reducing the rearrangements to COF which cause instability.

[0051] The advantages of the polymers of the invention can be summarized as follows:

- The reactivity of the new monomers allows to prepare copolymers having a very low content of carboxylic groups or derivatives thereof such $-\text{C}(\text{O})\text{F}$, $-\text{COO}-$. The carboxylic group content in the copolymer with TFE has resulted of about 10 times lower than that of a copolymer prepared under the same conditions but using PVE instead of fluorovinylethers (see the Examples). As said, the presence of a lower content of carboxylic groups, or of the corresponding derivatives (amides, esters, etc.) allows to obtain more stable polymers.
- The reactivity of the monomers of formula (I) is surprisingly high (see the Examples).
- To obtain amorphous polymers the amount of the vinyl ether of the invention must be such to lead to the disappearance of the crystalline domains. The skilled man in the art can easily find the amount of the vinyl ethers of the invention which is required for obtaining said results. Generally the amount of the vinyl ether for obtaining amorphous polymers is higher than 10% by moles, preferably in the range from about 15 to 20% by moles, or higher.
- The properties at low temperature (T_g) of the polymers of the invention result clearly better with respect both to copolymers having the same MVE content (see the Examples) and also, surprisingly, with respect to copolymers where the perfluorovinylether, the oxygen atoms being equal, does not show the $-\text{OCF}_2\text{O}-$ group directly bound to the unsaturation, as in the case of the $\text{CF}_2=\text{CFOCF}_2\text{CF}_2\text{OCF}_3$ (β -PDE) (see the Examples).
- A further advantage of the fluorovinylethers (I) of the invention, as hereinafter illustrated, consists in that their preparation is carried out in a continuous plant by a limited number of steps. Furthermore the used raw materials

are cheap. The following ones can for example be mentioned:

$\text{CF}_2(\text{OF})_2$, $\text{CF}_2=\text{CF}_2$, $\text{CF}_2=\text{CFOCF}_3$, $\text{CHCl}=\text{CFCl}$, $\text{CFCl}=\text{CFCl}$,
 $\text{CF}_2=\text{CFCl}$, $\text{CF}_2=\text{CFH}$, $\text{CF}_2=\text{CH}_2$, $\text{CHCl}=\text{CHCl}$ and other olefins.

The use of these reactants is specified in the synthesis process of the vinyl ethers of the invention.

[0052] The copolymers of the invention are obtainable by polymerizing with the suitable comonomers the fluorovinylethers of general formula (I)-(IV). To obtain the fluoroelastomers of the invention the amount of the comonomers of formula (I)-(IV) used in the comonomer mixture is such to lead to the disappearance of the crystalline domains. Generally the amount is higher than 10% by moles.


[0053] With copolymer, a polymer containing the vinyl ether of the invention and one or more comonomers, is meant.

[0054] With comonomers, fluorinated compounds having at least one polymerizable double bond $\text{C}=\text{C}$, optionally containing in the molecule hydrogen and/or chlorine and/or bromine and/or iodine and/or oxygen, are meant, said comonomers being able to produce (co)polymers in the presence of radical initiators.

[0055] Optional comonomers which can be copolymerized are non fluorinated C_2 - C_8 olefins, such as ethylene, propylene, isobutylene.

[0056] Among the usable comonomers the following can be mentioned:

- C_2 - C_8 perfluoroolefins, such as tetrafluoroethylene (TFE), hexafluoropropene (HFP), hexafluoroisobutene;
- C_2 - C_8 hydrogenated fluoroolefins, such as vinyl fluoride (VF), vinylidene fluoride (VDF), trifluoroethylene, $\text{CH}_2=\text{CH}-\text{R}_1^1$, perfluoroalkylethylenes wherein R_1^1 is a C_1 - C_6 perfluoroalkyl;
- C_2 - C_8 chloro- and/or bromo- and/or iodo-fluoroolefins, such as chlorotrifluoroethylene (CTFE) and bromotrifluoroethylene;
- $\text{CF}_2=\text{CFOR}_1^2$ (per)fluoroalkylvinylethers (PAVE), wherein R_1^2 is a C_1 - C_6 (per)fluoroalkyl, for example trifluoromethyl, bromodifluoromethyl or heptafluoropropyl;
- $\text{CF}_2=\text{CFOX}^a$ (per)fluoro-oxyalkylvinylethers, wherein X^a is a C_1 - C_{12} alkyl, or a C_1 - C_{12} oxyalkyl, or a C_1 - C_{12} (per)fluoroalkyl having one or more ether groups, for example perfluoro-2-propoxy-propyl.
- sulphonic monomers having the structure $\text{CF}_2=\text{CFOX}^b\text{SO}_2\text{F}$, wherein $\text{X}^b = \text{CF}_2\text{CF}_2$, $\text{CF}_2\text{CF}_2\text{CF}_2$, $\text{CF}_2\text{CF}(\text{CF}_2\text{X}^c)$ wherein $\text{X}^c = \text{F}$, Cl , Br .
- a bis-olefin having the general formula




wherein

R_1^1 , R_2^1 , R_3^1 , R_4^1 , R_5^1 , R_6^1 equal to or different from each other, are H or C_1 - C_5 alkyls;
 Z is a C_1 - C_{18} linear or branched alkylene or cycloalkylene radical, optionally containing oxygen atoms, preferably at least partially fluorinated, or a (per)fluoropolyoxy-alkylene radical.

In the formula (IA), Z is preferably a C_4 - C_{12} perfluoroalkylene radical, while R_1^1 , R_2^1 , R_3^1 , R_4^1 , R_5^1 , R_6^1 are preferably hydrogen.

[0057] When Z is a (per)fluoropolyoxyalkylene radical, it preferably has the formula:




wherein:

Q is a C_1 - C_{10} alkylene or oxyalkylene radical;

p is 0 or 1;

ma and na are integers such that the ma/na ratio is comprised between 0.2 and 5 and the molecular weight of said (per)fluoropolyoxyalkylene radical is in the range from 500 to 10,000, preferably from 1,000 to 4,000. Preferably,

Q is selected from the following groups:



with $s = 1-3$.

[0058] The bis-olefins of formula (IA) wherein Z is an alkylene or cycloalkylene radical can be prepared according to what described, for example, by I.L. Knunyants et al. in Izv. Akad. Nauk. SSR, Ser. Khim. 1964(2), 384-6, while the bis-olefins containing (per)fluoropolyoxyalkylene sequences are described in USP 3,810,874.

[0059] The amount of units in the chain deriving from said bis-olefins is generally in the range 0.01-1.0 by moles.

[0060] The above indicated comonomers, polymerizable with perfluorovinylethers, can be used separately or in admixture with other comonomers.

[0061] The base structure of the fluoroelastomer can in particular be selected from:

(1) copolymers based on VDF, wherein the latter is copolymerized with at least one comonomer selected from:

$\text{C}_2\text{-C}_8$ perfluoroolefins such as tetrafluoroethylene (TFE), hexafluoropropene (HFP); $\text{C}_2\text{-C}_8$ chloro- and/or bromo- and/or iodo-fluoroolefins, such as chlorotrifluoroethylene (CTFE) and bromotrifluoroethylene; $\text{CF}_2=\text{CFOR}_1^t$ (per)fluoroalkylvinylethers (PAVE), wherein R_1^t is a $\text{C}_1\text{-C}_6$ (per)fluoroalkyl, for example trifluoromethyl, bromodifluoromethyl, pentafluoropropyl; $\text{CF}_2=\text{CFOX}^t$ perfluoroalkylvinylethers, wherein X^t is a $\text{C}_1\text{-C}_{12}$ perfluoroalkyl having one or more ether groups, for example perfluoro-2-propoxy-propyl; $\text{C}_2\text{-C}_8$ non fluorinated olefins (OI), for example ethylene and propylene;

(2) copolymers based on TFE, where the latter is copolymerized with at least one comonomer selected from: $\text{CF}_2=\text{CFOR}_1^t$ (per)fluoroalkylvinylethers (PAVE), wherein R_1^t is as above defined; $\text{CF}_2=\text{CFOX}^t$ perfluoroalkylvinylethers, wherein X^t is as above defined; $\text{C}_2\text{-C}_8$ fluoroolefins containing hydrogen and/or chlorine and/or bromine and/or iodine atoms; $\text{C}_2\text{-C}_8$ non fluorinated olefins (OI).

[0062] Inside the above defined classes of fluoroelastomers, preferred base monomeric compositions (by moles) are the following:

VDF	45-85
HFP and/or PAVE	0-45
TFE	0-30
MOVE	1-45, preferably 5-40
OI	0-40

the sum of HFP+PAVE+MOVE being at most 45% ;

TFE	50-85
PAVE	0-50
MOVE	1-50, preferably 5-40
OI	0-40

the sum of PAVE+MOVE being at most 50.

[0063] The fluoroelastomers of the invention are preferably cured by peroxidic route.

[0064] When they are cured by ionic route, the preferred compositions (expressed by moles) are the following when the fluoroelastomer is used for the O-ring preparation:

VDF	48-65
HFP	20-35
PAVE	0-6
TFE	0-20
MOVE	3-9

the sum PAVE + MOVE lower than or equal to 10% by moles.

[0065] For the use of fluoroelastomers for obtaining shaft seals or fuel hoses the following compositions (by moles) are preferred:

VDF	30-47
HFP	20-40
PAVE	0-17
TFE	10-30
MOVE	3-20

the sum PAVE+MOVE lower than or equal to 20% by moles.


[0066] In the case of fluoroelastomers curable by peroxidic route, it is preferable to add small amounts of a bis-olefin as above mentioned.

[0067] In order to reach a good curing degree it is suitable to use fluoroelastomers containing reactive sites, i.e. iodine and/or bromine in chain, preferably iodine (cure site monomer).

[0068] Also an iodinated and/or brominated transfer agent can be used.

[0069] The process for the preparation of fluorinated polymers according to the present invention can be carried out by polymerization in organic solvent as described in USP 4,864,006 and 5,182,342, herein incorporated by reference. The organic solvent is selected from the group comprising chlorofluorocarbons, perfluoropolyethers, hydrofluorocarbons and hydrofluoroethers.

[0070] Alternatively the preparation of fluoroelastomers of the present invention can be carried out by copolymerization of the monomers in aqueous emulsion according to well known methods in the prior art, in the presence of radical initiators (for example alkaline or ammonium persulphates, perphosphates, perborates or percarbonates), optionally in combination with ferrous, cuprous or silver salts, or of other easily oxidizable metals. In the reaction medium also surfactants of various type are usually present, among which the fluorinated surfactants of formula:



are particularly preferred, wherein R^3 is a C_5 - C_{16} (per) fluoroalkyl chain or a (per)fluoropolyoxyalkyl chain, X^+ is $-COO^-$ or $-SO_3^-$, M^+ is selected from: H^+ , NH_4^+ , an alkaline metal ion. Among the most commonly used, ammonium perfluorooctanoate, (per)fluoropolyoxyalkylenes ended with one or more carboxylic groups, etc. can be mentioned.

See USP 4,990,283 and USP 4,864,006.

[0071] At the end of the polymerization, the fluoroelastomer is separated from the emulsion by conventional methods, such as coagulation by addition of electrolytes or by cooling.

[0072] Alternatively, the polymerization can be carried out in bulk or in suspension, in an organic liquid where a radical initiator is present, according to well known techniques.

[0073] The polymerization reaction is generally carried out at temperatures comprised between 25°C and 150°C, under pressure up to 10 MPa.

[0074] The preparation of the fluoroelastomers of the present invention is preferably carried out in aqueous emulsion in the presence of an emulsion, dispersion or microemulsion of perfluoropolyoxyalkylenes, according to USP 4,789,717 and USP 4,864,006.

[0075] The fluoroelastomers of the present invention are preferably cured by peroxidic route, wherefore they preferably contain in the chain and/or in terminal position of the macromolecules iodine and/or bromine atoms, preferably iodine. The introduction of such iodine and/or bromine atoms can be carried out by addition, in the reaction mixture, of brominated and/or iodinated cure-site comonomers, such as bromo and/or iodo olefins having from 2 to 10 carbon atoms (as described for example in USP 4,035,565 and USP 4,694,045), or iodo and/or bromo fluoroalkylvinylethers (as described in patents US 4,745,165, US 4,564,662 and EP 199,138), in amounts such that the content of cure-site comonomers in the final product is generally in the range 0.05-2 moles for 100 moles of the other base monomeric units.

[0076] Alternatively or also in combination with cure-site comonomers, it is possible to introduce iodine and/or bromine end atoms by addition to the reaction mixture of iodinated and/or brominated chain transfer agents, such as for example compounds of formula $R^b(I)_x(Br)_y$, wherein R^b is a (per)fluoroalkyl or a (per)fluorochloroalkyl having from 1 to 8 carbon atoms, while x and y are integers comprised between 0 and 2, with $1 \leq x+y \leq 2$ (see for example patents US 4,243,770 and US 4,943,622).

[0077] It is also possible to use as chain transfer agents iodides and/or bromides of alkaline or alkaline-earth metals, according to USP 5,173,553.

[0078] Alternatively or in combination with the chain transfer agents containing iodine and/or bromine, other chain transfer agents known in the prior art, such as ethyl acetate, diethylmalonate, etc., can be used.

[0079] Curing by peroxidic route is carried out, according to known techniques, by addition of a suitable peroxide able to generate radicals by heating.

[0080] Among the most commonly used we remind: dialkylperoxides, such as for example di-terbutyl-peroxide and 2,5-dimethyl-2,5-di(terbutylperoxy)hexane; dicumyl peroxide, dibenzoyl peroxide; di-terbutyl perbenzoate; di-[1,3-dimethyl-3-(terbutylperoxy)butyl]carbonate. Other peroxidic systems are described, for example, in European patent applications EP 136,596 and EP 410,351.

[0081] To the curing blend other compounds are then added, such as:

(a) curing coagents, in amounts generally in the range 0.5-10%, preferably 1-7%, by weight with respect to the polymer; among them: triallyl-cyanurate, triallylisocyanurate (TAIC), tris(diallylamine)-s-triazine; triallylphosphite; N,N-diallyl-acrylamide; N,N,N',N'-tetraallyl-malonamide; tri-vinyl-isocyanurate; and 4,6-tri-vinyl-methyltrisiloxane, etc. are commonly used: TAIC is particularly preferred;

(b) a metal compound, in amounts in the range 1-15%, preferably 2-10%, by weight with respect to the polymer, selected from oxides and hydroxides of divalent metals, such as for example Mg, Zn, Ca or Pb, optionally combined with a weak acid salt, such as for example stearates, benzoates, carbonates, oxalates or phosphites of Ba, Na, K, Pb, Ca;

(c) other conventional additives, such as thickeners, pigments, antioxidants, stabilizers and the like.




[0082] The fluoroelastomers of the present invention can be cured by ionic route. Suitable well known in the art curing and accelerating agents are added to the curing blend, besides the above mentioned products at points (b) and (c). For example, as curing agents aromatic or aliphatic polyhydroxylated compounds, or derivatives thereof can be used, as described for example in EP 335,705 and USP 4,233,427. Among them it can in particular be mentioned: di-, tri- and tetrahydroxybenzenes, naphthalenes or anthracenes; bisphenols wherein the two aromatic rings are linked each other by an aliphatic, cycloaliphatic or aromatic bivalent radical, or by one oxygen or sulphur atom, or also one carbonyl group. The aromatic rings can be replaced with one or more chlorine, fluorine, bromine atoms, or with carbonyl, alkyl, acyl.

[0083] As accelerants it can for example be used: ammonium, phosphonium, arsonium or antimony quaternary salts (see for example EP 335,705 and USP 3,876,654); amino-phosphonium salts (see for example USP 4,259,463); phosphoranes (see for example USP 3,752,787); the iminic compounds described in EP 182,299 and EP 120,462; etc. Also adducts between an accelerant and a curing agent can be used, see patents US 5,648,429, US 5,430,381, US 5,648,430 herein incorporated by reference.

[0084] It is also possible to use systems of mixed, both ionic and peroxidic, curing, as described in EP 136,596.

[0085] The synthesis process of the new (per)fluorovinylethers, which comprises the reaction of the hypofluorite with a fluorinated olefin of formula $R_1R_2C=CR_3R_4$ to give the intermediate hypofluorite $F-CR_1R_2-CR_3R_4-OCF_2OF$, the subsequent reaction of said compound with a second fluorinated olefin of formula $R_5R_6C=CR_7R_8$ to give the intermediate $F-CR_1R_2-CR_3R_4-OCF_2O-CR_5R_6-CR_7R_8-F$ which by dehalogenation or dehydrohalogenation leads to the new perfluorovinylethers.

[0086] The general scheme of the synthesis is the following:



[0087] In this synthesis scheme:

- with reference to the formula of the compound (VII):

- R_1, R_4 , equal or different, are H, F; R_2, R_3 , equal or different are H, Cl under the following conditions: (1) when the final reaction is a dehalogenation $R_2, R_3 = \text{Cl}$, (2) when the final reaction is a dehydrohalogenation one of the two substituents R_2, R_3 is H and the other is Cl;

5 - R_5, R_6, R_7, R_8 are :

- F, or one of them is a C_1 - C_4 linear or branched perfluoroalkyl group, or a C_1 - C_4 linear or branched perfluoroalkoxy group containing from one to three oxygen atoms, or R_5 and R_7 , or R_6 and R_8 , are linked each other to form with C^2 and C^1 a C_5 - C_6 cycle perfluoroalkyl group;
- 10 - when one of the R_5 to R_8 radicals is a C_2 - C_4 linear or branched fluoroalkyl, or a C_2 - C_4 linear or branched fluoroalkoxy group containing from one to three oxygen atoms, one or two of the other R_5 to R_8 are F and one or two of the remainders, equal to or different from each other, are selected from H, Cl, Br, Iodine; when the substituents selected from H, Cl, Br, Iodine are two, they are both linked to the same carbon atom; when R_5 and R_7 , or R_6 and R_8 , are linked each other to form with C^2 and C^1 a C_5 - C_6 cycle fluoroalkyl group, one of the two free substituents R_6, R_8 or R_5, R_7 is F and the other is selected from H, Cl, Br, Iodine.
- the fluoroalkene used in the reaction a) is replaceable with that of the subsequent reaction b); in this case the meanings defined for the substituents of the R_1 - R_4 group, and respectively of the R_5 - R_8 group, are interchangeable each other, with the proviso that the position of each radical of each of the two groups R_1 - R_4 and R_5 - R_8 with respect to $-\text{OCF}_2\text{O}-$ on the chain of the intermediate compound (VII), is the same which is occupied if the synthesis takes place according to the above reported scheme and the two olefins each react in the considered steps.

[0088] In the first reaction a) of the above illustrated scheme a hypofluorite gas flow $\text{CF}_2(\text{OF})_2$, suitably diluted with an inert fluid, comes into contact, in a suitable reactor with outlet, on the bottom of the same (first reactor), with a flow of the $R_1R_2C=CR_3R_4$ olefin, optionally diluted in an inert fluid, so as to allow the chemical reaction a) with formation of the intermediate hypofluorite (VI). To favour the reaction stoichiometry, the reactants must be introduced into the reactor in an approximately unitary molar ratio, or with an excess of $\text{CF}_2(\text{OF})_2$. The residence time of the mixture in the reactor can range from few hundredths of second up to about 120 seconds depending on the olefin reactivity, the reaction temperature and the presence of optional reaction solvents.

[0089] The reaction temperature can range from -40° to -150°C , preferably from -80° to -130°C .

[0090] The compound (VI) usually is not separated from the reaction product and it is transferred in a continuous way to the subsequent reaction described in step b).

[0091] The mixture of the products coming out from the first reactor can be heated at room temperature before being fed into the second reactor.


[0092] In the second reaction b) the second olefin $R_5R_6C=CR_7R_8$ pure or in solution, reacts with the product obtained in the first reaction with formation of compound (VII).

[0093] The olefin can be fed in a continuous way, so as to maintain its concentration constant in the reactor. The temperature of the reaction b) can range from -20° to -130°C , preferably from -50° to -100°C . The olefin concentration is higher than or equal to 0.01M, preferably the concentration is higher than 3M, more preferably also the pure compound can be used.

[0094] The solvents used in steps a) and b) are perfluorinated or chlorohydrofluorinated solvents or hydrofluorocarbons. Examples of said solvents are: CF_2Cl_2 , CFCl_3 , $\text{CF}_3\text{CF}_2\text{H}$, CF_3CFH_2 , $\text{CF}_3\text{CF}_2\text{CF}_3$, $\text{CF}_3\text{CCl}_2\text{H}$, $\text{CF}_3\text{CF}_2\text{Cl}$.

In the reaction c) the compound (VII), dependently on the olefins used in steps a) and b), after distillation from the reaction product, is subjected to dechlorination or to dehydrochlorination to obtain the vinyl ethers of formula (I). This last step can be carried out by using reactions widely described in the prior art. The suitable selection of the substituents R_1 to R_8 in the two olefins used in the synthesis allows to obtain the vinyl ethers of the present invention.

[0095] Another object of the invention is a process wherein a hypofluorite of formula $X_1X_2C(\text{OF})_2$ wherein X_1 and X_2 equal or different are F, CF_3 , and two fluoroalkenes of formula respectively $\text{R}^A_1\text{R}^A_2C=\text{CR}^A_3\text{R}^A_4$ and $\text{R}^A_5\text{R}^A_6C=\text{CR}^A_7\text{R}^A_8$, wherein R^A_1 - R^A_8 equal or different, are F, H, Cl, Br, I, $-\text{CF}_2\text{OSO}_2\text{F}$, $-\text{SO}_2\text{F}$, $-\text{COF}$, C_1 - C_5 linear or branched perfluoroalkyl or oxyperfluoroalkyl group, are reacted according to steps a) and b), excluding the dehalogenation or dehydrohalogenation step, to obtain compounds of general formula (VIII)



[0096] The following Examples are reported with the purpose to illustrate the invention and they do not limit the scope of the same.

[0097] In the Examples the thermogravimetric analysis TGA is carried out by using a $10^\circ\text{C}/\text{min}$ rate.

EXAMPLE 1Synthesis of $\text{CF}_3\text{CF}_2\text{OCF}_2\text{OCFCICF}_2\text{Cl}$ perfluoro-1,2-dichloro-3,5-dioxaheptane.

- 5 **[0098]** The used reactor is of cylindrical type, with a total volume of 300 ml and is equipped with magnetic dragging mechanical stirrer, turbine with recycle of the reacting gas placed at 20 cm from the reactor top, internal thermocouple, two internal copper pipes for the reactant feeding which end at about 1 mm from the turbine, and product outlet from the bottom. In the reactor, inside which the temperature is maintained at -114°C , 1.1 l/h (litres/hour) of $\text{CF}_2(\text{OF})_2$ and 3.3 l/h of He are introduced through one of the two inlet pipes; A flow of 1.1 l/h of $\text{CF}_2=\text{CF}_2$ and 0.7 l/h of He is maintained through the second inlet pipe. Feeding is continued for 6.6 hours.
- 10 **[0099]** The residence time of the transport gas in the reaction zone comprised between the outlet of the two feeding pipes in the reactor and the inlet of the discharge pipe is of about 4 sec.
- [0100]** On the reactor bottom the reaction products are brought to room temperature and the gaseous mixture flow, monitored by gaschromatography, is fed in a continuous way, under mechanical stirring, into a second reactor having
- 15 a 250 ml volume maintained at the temperature of -70°C , equipped with mechanical stirrer, thermocouple, dipping inlet for the reacting mixture, outlet with head of inert gas. The reactor contains 72.6 g of dichlorodifluoroethylene $\text{CFCI}=\text{CFCl}$.
- [0101]** At the end of the addition of reacting gases into the second reactor, the reaction raw material is distilled by a plate column at atmospheric pressure, collecting 41.5 g of the desired product (boiling point 91°C).
- 20 **[0102]** The yield of perfluoro-1,2-dichloro-3,5-dioxaheptane, calculated with respect to $\text{CF}_2(\text{OF})_2$, is of 36%.

Characterization of perfluoro 1,2, dichloro-3,5-dioxaheptane.

- [0103]** Boiling point at atmospheric pressure: 91°C .
- 25 **[0104]** ^{19}F -NMR spectrum in p.p.m. (with respect to $\text{CFCl}_3 = 0$):
 $-51.3/-53.0$ (2F, O- CF_2 -O); $-70.6/-72.6$ (2F, C- CF_2Cl); $-78.0/-78.4$ (1F, O- CFCl -C); -87.8 (3F, CF_3 -C); $-90.2/-91.8$ (2F, C- CF_2 -O).
- [0104]** Mass spectrum (E.I. electronic impact), main peaks and respective intensities:
 69 (48.6%); 119 (84.3%); 151 (76.8%); 153 (69.8%); 185 (100%).
- 30 **[0105]** IR spectrum (cm^{-1}) intensity: (w) =weak, (m) =medium, (s)=strong, (vs)=very strong:
 1407.3 (w); 1235.8 (vs); 1177.7 (vs); 1097.5 (vs); 1032.2 (s); 929.3 (w); 847.9 (m).

EXAMPLE 2

- 35 Synthesis of $\text{CF}_3\text{OCF}_2\text{CF}_2\text{OCF}_2\text{OCFCICF}_2\text{Cl}$ perfluoro-1,2-dichloro-3,5,8-trioxanonane (isomer A) and of $\text{CF}_3\text{OCF}(\text{CF}_3)\text{OCF}_2\text{OCFCICF}_2\text{Cl}$ perfluoro-1,2-dichloro-3,5,7-trioxa-6-methyloctane (isomer B)

- [0106]** In a reactor identical to that used in Example 1, maintained at the same temperature of -114°C , 1.55 l/h of $\text{CF}_2(\text{OF})_2$ and 4.5 l/h of He are introduced through one of the two inlet pipes; through the second inlet pipe 1.4 l/h of $\text{CF}_2=\text{CF}-\text{OCF}_3$ and 0.7 l/h of He for 4.5 hours.
- 40 **[0107]** The residence time of the transport gas in the reaction zone comprised between the reactor outlet and the end of the two feeding pipes is of about 3 sec.
- [0108]** On the reactor bottom the reaction products are brought to room temperature and the gaseous mixture flow, monitored by gaschromatography, is fed in a continuous way, under mechanical stirring, into a second reactor identical
- 45 to the one used for the same step in Example 1. Inside, where a temperature of -70°C is maintained, there are 51 g of dichlorodifluoroethylene $\text{CFCI}=\text{CFCl}$.
- [0109]** At the end of the addition of the reacting gases into the second reactor, the reaction raw material is distilled by a plate column at the reduced pressure of 250 mmHg. 50 g of a mixture formed by two isomers, respectively, isomer A) perfluoro-1,2-dichloro-3,5,8-trioxanonane and isomer B) perfluoro-1,2-dichloro-3,5,7-trioxa-6-methyloctane are collected.
- 50 The mixture composition is determined by gaschromatography and is the following: isomer A 79%, isomer B 21%. The molar yield of A+B with respect to the used $\text{CF}_2(\text{OF})_2$ is 38%. The molar yield of A+B with respect to the used perfluoromethylvinylether is 42%. The isomers have been separated by preparative gaschromatography.

Characterization of products A and B

- 55 **[0110]** Mixture boiling point (A 79%, B 21%) at the reduced pressure of 250 mmHg: 82°C .
- [0111]** ^{19}F -NMR spectrum in p.p.m. (with respect to $\text{CFCl}_3=0$) of the isomer A:
 $-50.6/-52.4$ (2F, O- CF_2 -O); $-70.0/-71.8$ (2F, C- CF_2Cl); -77.7 (1F, O- CFCl -C); $-55.3/-55.6$ (3F, CF_3 -OC); -

EP 1 148 072 A2

90.7/-91.1 (2F, C-OCF₂-C) ; -90.2/-90.6 (2F, C-OC-CF₂OCOC).

[0112] ¹⁹F-NMR spectrum in p.p.m. (with respect to CFCI₃=0) of isomer B:

-50.0/-52.1 (2F, O-CF₂-O) ; -70.0/-71.8 (2F, C-CF₂Cl) ; -77.9 (1F, O-CFCl-C) ; -54.6/-54.9 (3F, CF₃OC) ; -85.7/-86.1 (3F, OC(CF₃)O) ; -100.3/-101.0 (1F, OCF(C)O).

5 [0113] Mass spectrum (electronic impact), main peaks and respective intensities:

Product A: 69 (50) ; 119 (100) ; 151 (50) ; 185 (42) ; 251 (38) ;

Product B: 69 (96) ; 97 (50) ; 135 (42) ; 151 (92) ; 185 (100).

10 [0114] IR spectrum (cm⁻¹), intensity of the mixture A 79%, B 21%:

(w)=weak, (m)=medium, (s)=strong, (vs)=very strong:

1388 (w) ; 1288 (vs) ; 1233 (vs) ; 1151 (vs) ; 1104 (vs) ; 1032 (s) ; 846 (m) ; 685 (w) .

EXAMPLE 3

15

Synthesis of CF₃OCF₂CF₂OCF₂OCHClCHFCI perfluoro-1,2-dichloro 1,2-dihydro-3,5,8-trioxanonane (isomer C) and of CF₃OCF(CF₃)OCF₂OCHClCHFCI perfluoro-1,2-dichloro-1,2-dihydro-3,5,7-trioxa-6-methyloctane (isomer D).

20 [0115] In a reactor identical to that used in Example 1, maintained at the temperature of -112°C, 1.55 l/h of CF₂(OF)₂ and 4.5 l/h of He are introduced through one of the two inlet pipes; through the second inlet pipe 1.4 l/h of CF₂=CF-OCF₃ and 0.7 l/h of He for 5 hours.

[0116] The residence time of the transport gas in the reaction zone comprised between the reactor outlet and the end of the two feeding pipes is of about 3 sec.

25 [0117] On the reactor bottom the reaction products are brought to room temperature and the gaseous mixture flow, monitored by gaschromatography, is fed in a continuous way, under mechanical stirring, into a second reactor identical to the one used for the same step in Example 1. Inside, the temperature is of -70°C and there are 50 g of 1,2-dichloroethylene CClH=CClH and 50 g of CFCI₃.

30 [0118] At the end of the addition of the reacting gases into the second reactor, after distillation of the solvent at room pressure, the reaction raw material is distilled by a plate column at the reduced pressure of 100 mmHg. 43.5 g of the mixture of the desired products (isomer C 78%, isomer D 22%, determined by gaschromatography) are collected. The molar yield of C+D with respect to the used CF₂(OF)₂ is 33%. The isomers have been separated by preparative gaschromatography.

Characterization of products C and D

35

[0119] Mixture boiling point (C 78%, D 22%) at the reduced pressure of 100 mmHg: 71°C.

[0120] ¹⁹F-NMR spectrum in p.p.m. (with respect to CFCI₃= 0) of the isomer C perfluoro-1,2-dichloro-1,2-dihydro-3,5,8-trioxanonane:

40 -56.0/-57.2 (2F, O-CF₂-O) ; -143.2/-146.0 (1F, C-CHFCI) ; -55.8 (3F, CF₃-OC) ; -91.0/-91.4 (2F, C-OCF₂-C) ; -90.3/-90.5 (2F, C-OC-CF₂OCOC).

[0121] ¹⁹F-NMR spectrum in p.p.m. (with respect to CFCI₃=0) of the isomer D perfluoro-1,2-dichloro-1,2-dihydro-3,5,7-trioxa-6-methyloctane:

-56.0/-57.2 (2F, O-CF₂-O) ; -143.2/-146.0 (1F, C-CHFCI) ; -54.9/-55.1 (3F, CF₃-OC) ; -86.2/-86.3 (3F, OC(CF₃)O) ; -100.5/-101.0 (1F, OCF(C)O).

45 [0122] ¹H spectrum in p.p.m. (with respect to TMS) of the isomers C and D: 6.28/6.05 (1H -CHFCI) ; 6.02/5.95 (1H -CHCl-)

[0123] Mass spectrum (electronic impact), main peaks and respective intensities %:

69 (84) ; 119 (100) ; 185 (51.1) ; 251 (84) ; 281 (15.8) ; 283 (4.8) ; 347 (5.7) ; 349 (1.7).

[0124] IR spectrum (cm⁻¹) intensity : (w)=weak, (m)=medium, (s)=strong, (vs)=very strong:

50 3001.0 (w) ; 2920.9 (w) ; 2850.9 (w) ; 1286.3 (vs) ; 1233.7 (vs) ; 1125.5 (vs) ; 1081.8 (s) ; 1047.9 (s) ; 815.9 (m) ; 766.3 (m).

EXAMPLE 4

Dealogenation of perfluoro 1,2-dichloro-3,5-dioxaheptane

55

[0125] In a 25 ml three-necked flask, equipped with mechanical stirrer, thermometer, dropping funnel, distillation column equipped with water refrigerant and collecting trap maintained at -78°C and connected to a mechanical vacuum pump, 150 ml of DMF, 15 g of Zn in powder, 0.5 g of K₂CO₃ and 100 mg of I₂ are introduced. The internal temperature

EP 1 148 072 A2

is brought to 80°C and 50 g of perfluoro-1,2-dichloro-3,5-dioxahexane are added drop by drop.

[0126] When the addition is over the mixture is allowed to react for about 30 minutes. At the end the internal pressure is gradually brought from starting 760 mmHg to 300 mmHg. After about 20 minutes the collecting trap containing 34.2 g of perfluoro-3,5-dioxo-1-heptene (MOVE 1) is disconnected.

[0127] The dehalogenation yield is 85%.

Characterization of perfluoro-3,5-dioxo-1-heptene (MOVE 1)

[0128] Boiling point at atmospheric pressure: 41.9°C.

[0129] ^{19}F -NMR spectrum in p.p.m. with respect to $\text{CFCl}_3=0$:

-56.8 (2F, O-CF₂-O); -87.2 (3F, CF₃-C); -90.6 (2F, C-CF₂-O); -114 (1F, O-C=C-F); -121.8 (1F, O-C=CF); -137 (1F, O-C-F=C);

[0130] Mass spectrum (electronic impact), main peaks and respective intensities:

69 (66.5%); 119 (100%); 147 (83.4%); 185 (89.4%); 216 (67.3%); 282 (8.2%).

[0131] IR spectrum (cm⁻¹) intensity: (w)=weak, (m)=medium, (s)=strong, (vs)=very strong:

1839.5 (m); 1407.6 (w); 1307.4 (vs); 1245.8 (vs); 1117.4 (vs); 907.2 (m); 846.0 (m).

EXAMPLE 5

Dehalogenation of the isomer mixture A+B obtained in Example 2 (perfluoro-1,2-dichloro-3,5,8-trioxanonane $\text{CF}_3\text{OCF}_2\text{CF}_2\text{OCFClCF}_2\text{Cl}$ + perfluoro-1,2-dichloro-3,5,7-trioxa-6-methyloctane $\text{CF}_3\text{OCF}(\text{CF}_3)\text{OCF}_2\text{OCFClCF}_2\text{Cl}$).

[0132] In a 250 ml flask equipped as described in the previous Example 4, 110 ml of DMF, 10 g of Zn in powder and 0.3 ml of Br₂ are introduced. The internal temperature is brought to 75°C and 30.3 g of the binary mixture A+B separated in the previous Example 2 are added drop by drop. When the addition is over the mixture is allowed to react for about 3 hours. At the end the internal pressure is gradually lowered from 760 mmHg to 200 mmHg at -79°C. After about 30 minutes the collecting trap is disconnected. The corresponding content, which is washed with water, is recovered. At the end 24.0 g of a mixture formed for 79% (gaschromatographic determination) by perfluoro-3,5,8-trioxa-1-nonene (MOVE 2) $\text{CF}_3\text{OCF}_2\text{CF}_2\text{OCF}_2\text{OCF}=\text{CF}_2$ (isomer A') and for 21% by perfluoro-3,5,7-trioxa-6-methyl-1 octene (MOVE 2a) $\text{CF}_3\text{OCF}(\text{CF}_3)\text{OCF}_2\text{O}-\text{CF}=\text{CF}_2$ (isomer B') are obtained, which are then separated by preparative gaschromatography.

Characterization of products A' and B'

[0133] Boiling range of the isomer mixture at atmospheric pressure: 72.5°-74.5°C.

[0134] ^{19}F -NMR spectrum in p.p.m. (with respect to $\text{CFCl}_3=0$) of the isomer A':

-55.9 (3F, CF₃-O); -56.9 (2F, O-CF₂-O); -90.8 (2F, C-CF₂-O); -91.2 (2F, O-CF₂-C); -114 (1F, O-C=C-F); -121.8 (1F, O-C=CF); -137 (1F, O-CF=C)

[0135] ^{19}F -NMR spectrum in p.p.m. (with respect to $\text{CFCl}_3=0$) of the isomer B':

-55.9 (3F, CF₃-O); -56.2 (2F, O-CF₂-O); -86.4 (3F, CF₃-C); -100.9 (1F, CF); -114 (1F, O-C=C-F); -122 (1F, O-C=CF); -137 (1F, O-CF=C).

[0136] Mass spectrum (electronic impact), main peaks and respective intensities of the isomer A':

69 (74); 81 (18); 119 (100); 147 (59); 185 (26); 251 (21);

[0137] Mass spectrum (electronic impact), main peaks and respective intensities of the isomer B':

69 (80); 81 (37); 97 (47); 119 (36); 147 (100); 185 (19).

[0138] IR spectrum (cm⁻¹), intensity: (w)=weak, (m)=medium, (s)=strong, (vs)=very strong, 1839 (m); 1343 (s); 1248 (vs); 1145 (vs); 918 (m); 889 (m).

EXAMPLE 6

Dehalogenation of the isomers C+D mixture obtained in Example 3 ($\text{CF}_3\text{OCF}_2\text{CF}_2\text{OCF}_2\text{OCHClCHFCI}$ perfluoro-1,2-dichloro-1,2-dihydro-3,5,8-trioxanonane (isomer C) + $\text{CF}_3\text{OCF}(\text{CF}_3)\text{OCF}_2\text{OCHClCHFCI}$ perfluoro-1,2-dichloro-1,2-dihydro-3,5,7-trioxa-6-methyloctane (isomer D)).

[0139] In a 500 ml three-necked flask, equipped with mechanical stirrer, thermometer, dropping funnel, distillation column having a water refrigerant and a collecting trap maintained at the temperature of -78°C, 250 ml of DMF, 30 g of zinc in powder and 300 mg of I₂ are introduced.

[0140] The temperature is brought to 100°C and 56.9 g of the isomer mixture obtained in Example 3 are added drop by drop.

[0141] When the addition is over the reactor internal temperature is brought to 120°C and stirring is maintained for 24 hours. At the end the reaction product, which contains traces of solvent and which is collected in the trap maintained at -78°C, is distilled. After washing with water 35 g of a mixture of perfluoro-1,2-dihydro-3,5,8-trioxa-1-nonene (isomer C', 79% by moles) and of perfluoro-1,2-dihydro-3,5,7-trioxa-5-methyl-1-octene (isomer D', 21% by moles) are recovered. The isomers are separated by preparative gaschromatography.

[0142] The dehaloagenation reaction yield is 76%.

10 Characterization of products C' and D'

[0143] Boiling range of the mixture of isomers C' 79%, D' 21% at atmospheric pressure: 90.0°-92.0°C.

[0144] ¹⁹F-NMR spectrum in p.p.m. (with respect to CFC1₃=0) of the isomer C' perfluoro-1,2-dihydro-3,5,8-trioxa-1-nonene:

15 -55.7 (3F, CF₃-O) ; -57.3 (2F, O-CF₂-O) ; -90.9 (2F, C-CF₂-O) ; -91.2 (2F, O-CF₂-C) ; -149.3/-150.0 (1F, O-C=C-F).

[0145] ¹⁹F-NMR spectrum in p.p.m. (with respect to CFC1₃=0) of the isomer D' perfluoro-1,2-dihydro-3,5,7-trioxa-6-methyl-1-octene:

20 -55.0 (3F, CF₃-O) ; -56.9 (2F, O-CF₂-O) ; -86.2 (3F, CF₃-C) ; -101.0 (1F, CF) ; -149.3/-150.0 (1F, O-C=C-F)

[0146] Mass spectrum (electronic impact), main peaks and respective intensities %:

69 (82) ; 119 (100) ; 185 (29) ; 246 (25) ; 251 (20) ; 312 (43).

[0147] IR spectrum (cm⁻¹) intensity of the isomer mixture (C' 79%, D' 21%) : (w)=weak, (m)=medium, (s)=strong, (vs)=very strong:

3140 (w) ; 1722 (w) ; 1695 (w) ; 1402 (m) ; 1281 (vs) ; 1237 (vs) ; 1147 (vs) ; 1106 (vs) ; 1030 (m).

25 EXAMPLE 7

Homopolymerization of perfluoro-3,5-dioxa-1-heptene (MOVE 1).

30 [0148] In a glass reactor for polymerizations, having a 20 ml volume, equipped with magnetic stirring and with an inlet for the reactant feeding and discharge, 60 µl of perfluoropropionylperoxide at 3% by weight in CFC1₂CF₂Cl and 3 g of MOVE 1 are in sequence introduced. The so charged reactor is brought to the temperature of -196°C, evacuated, brought to room temperature, the all twice. At the end of the degassing operations the reactor is thermostated at the temperature of 30°C and the mixture is allowed to react under these conditions for two days under magnetic stirring.

35 [0149] The reaction raw material which is finally recovered appears as a slightly viscous, transparent, colourless and homogeneous solution.

[0150] After distillation of the unreacted monomer, and subsequent stripping under vacuum at 150°C for 3 hours, 180 mg of the polymer are separated.

40 [0151] The IR analysis of the obtained polymer shows that, in the spectrum, absorption bands in the zone of the fluorinated double bonds are absent.

[0152] The ¹⁹F-NMR analysis carried out on the polymer dissolved in C6F6 is in accordance with the homopolymer structure having a molecular weight of 50,000. The analysis does not show the presence of unreacted monomer.

45 [0153] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The polymer T_g, determined by DSC, is -35.4°C. The thermogravimetric analysis (TGA) shows a weight loss of 2% at 332°C and of 10% at 383°C.

EXAMPLE 8

50 Copolymer between perfluoro-3,5,8-trioxa-1-nonene CF₃OCF₂CF₂OCF₂OCF=CF₂ (MOVE 2) and perfluoro-3,5,7-trioxa-6, methyl-1-octene CF₃OCF(CF₃)OCF₂O-CF=CF₂ (MOVE 2a).

55 [0154] In a reactor having the same characteristics as that described in Example 7, 150 µl of perfluoropropionylperoxide at 3% by weight in CFC1₂CF₂Cl and 3.2 g of a mixture prepared according to the process of Example 5 and containing 83% MOVE 2 and 17% MOVE 2a, are introduced. The reactor is then evacuated, cooled, and the subsequent reaction carried out as described in the previous Example 7.

[0155] The reaction raw material appears as a slightly viscous, transparent, colourless and homogeneous solution. The monomers which have not reacted are distilled and a stripping under vacuum at 150°C for 3 hours is in sequence carried out. Finally 350 mg of the polymer are separated.

[0156] The IR analysis shows that, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds are absent.

[0157] The ^{19}F -NMR analysis is in accordance with the copolymer structure having an average molecular weight of 35,000 and a MOVE 2/MOVE 2a content equal to the percentages of the reacting mixture; unreacted monomers are not evident.

[0158] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The polymer T_g , determined by DSC, is -52.6°C . The thermogravimetric analysis (TGA) shows a weight loss of 2% at 280°C and of 10% at 327°C .

EXAMPLE 9

Amorphous copolymer between MOVE 1 and TFE.

[0159] In an AISI-316 polymerization reactor having a 40 ml volume, equipped with magnetic stirring, pressure transducer and an inlet for the reactant feeding and discharge, 250 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{CF}_2\text{Cl}$, 9.8 mmoles of MOVE 1 and 18 mmoles of tetrafluoroethylene are introduced.

[0160] The reactor is cooled to the temperature of -196°C , evacuated, then brought to room temperature and cooled again, the all twice.

[0161] At the end of the degassing operations the reactor is thermostated at the temperature of 30°C and the reaction mixture maintained under magnetic stirring. The internal pressure decreases from 6.4 atm to 4.7 atm in about 8 hours (reaction time).

[0162] After distillation of the unreacted monomers, and polymer stripping under vacuum for 3 hours at 150°C , 1,100 mg of polymer are recovered, which appears as a transparent and colourless rubber.

[0163] By ^{19}F -NMR analysis of the polymer dissolved under heating in C_6F_6 it is determined that the MOVE 1 molar percentage in the polymer is 24%.

[0164] The IR analysis does not show, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds, and shows the presence of very small absorption bands in the zone of the carboxyl signals. The intensity of these signals, compared with the similar ones obtained from a film having the same thickness obtained with the polymer of the comparative Example 1, is equal to about 1/10 of these latter.

[0165] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The T_g determined by DSC is -21.4°C .

[0166] The TGA shows a weight loss of 2% at 450°C and of 10% at 477°C . The polymer therefore results thermally more stable with respect to the comparative Example (see afterwards).

[0167] The polymer intrinsic viscosity measured at 30°C in Fluorinert® FC-75, is 35.5 ml/g.

EXAMPLE 10

Amorphous copolymer between MOVE 1 and TFE.

[0168] In an AISI-316 polymerization reactor identical to that described in the previous Example 9, 250 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{CF}_2\text{Cl}$, 9.75 mmoles of MOVE 1 and 9 mmoles of tetrafluoroethylene are in sequence introduced.

[0169] The procedure already described in the previous Example 9 is then followed until the thermostating step at the temperature of 30°C under magnetic stirring. During the reaction the internal pressure decreases from 3.4 atm to 2.9 atm in about 8 hours.

[0170] At the end the unreacted monomers are distilled and the polymer is stripped under vacuum at 150°C for 3 hours.

[0171] 480 mg of the polymer are separated.

[0172] By ^{19}F -NMR analysis of the polymer dissolved under heating in C_6F_6 it is determined that the MOVE 1 molar percentage in the polymer is 39%.

[0173] The IR analysis shows that, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds are absent.

[0174] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The T_g determined by DSC is -29.8°C .

[0175] The TGA shows a weight loss of 10% at 435°C .

EXAMPLE 11Amorphous copolymer between MOVE 1 and $\text{CF}_2=\text{CH}_2$

- 5 [0176] In a polymerization reactor identical to that described in Example 9, 250 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{CF}_2\text{Cl}$, 10 mmoles of MOVE 1 and 18 mmoles of VDF are in sequence introduced.
- [0177] The procedure already described in the previous Example 9 is followed until the thermostating step at the temperature of 30°C under magnetic stirring. The internal pressure decreases from 6.8 atm to 5.0 atm during the reaction (about 8 hours).
- 10 [0178] After distillation of the unreacted monomers, and subsequent polymer stripping under vacuum at 150°C for 3 hours, 1,600 mg of the polymer are separated, appearing as a transparent and colourless rubber.
- [0179] By the ^{19}F -NMR analysis carried out on the polymer dissolved in C_6F_6 it is determined that the MOVE 1 molar percentage in the polymer is 40%.
- [0180] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The T_g determined by DSC, is -47°C.
- 15 [0181] The TGA shows a weight loss of 2% at 428°C and of 10% at 455°C.

EXAMPLE 12Amorphous terpolymer MOVE 2/MOVE 2a/TFE.

- [0182] In a polymerization reactor identical to that described in Example 9, 100 μl of perfluoropropionylperoxide at 6% by weight in $\text{CFCl}_2\text{CF}_2\text{Cl}$, 10 mmoles of a MOVE 2 (83%) and MOVE 2a (17%) mixture synthesized according to the process of Example 5, and 18 mmoles of tetrafluoroethylene (TFE) are in sequence introduced.
- 25 [0183] The procedure already described in the previous Example 9 is then followed until thermostating at the temperature of 30°C under magnetic stirring. The internal pressure decreases from 6.1 atm to 3.9 atm during the reaction (about 8 hours).
- [0184] After distillation of the unreacted monomers and polymer stripping under vacuum at 150°C for 3 hours, the polymer is separated.
- 30 [0185] By the ^{19}F -NMR analysis carried out on the polymer dissolved in C_6F_6 it results that the total molar percentage of the MOVE 2 + MOVE 2a perfluorovinylethers in the polymer is 22%; the MOVE 2/MOVE 2a ratio by moles in the polymer is 83/17 and it is equal to that of the starting fed mixture.
- [0186] The presence of unreacted monomers is not evident.
- [0187] The IR analysis does not show, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds, and it shows the presence of very small absorption bands in the zone of the carboxyl signals. The intensity of these signals, compared with the similar ones obtained from a film having the same thickness obtained with the polymer of the comparative Example 1, is equal to about 1/10 of the latter.
- 35 [0188] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The T_g determined by DSC, is -37.5°C.
- 40 [0189] The TGA shows a weight loss of 10% at 473°C.
- [0190] The polymer intrinsic viscosity measured at 30°C in Fluorinert® FC-75, is 40.0 ml/g.

EXAMPLE 13Amorphous terpolymer MOVE 2/MOVE 2a/TFE.

- [0191] In a polymerization reactor identical to that described in Example 9, 100 μl of perfluoropropionylperoxide at 6% by weight in $\text{CFCl}_2\text{CF}_2\text{Cl}$, 9.7 mmoles of the MOVE 2 (83%) and MOVE 2a (17%) mixture synthesized according to the process of Example 5, and 10 mmoles of tetrafluoroethylene (TFE) are in sequence introduced.
- 50 [0192] The procedure already described in the previous Example 9 is then followed until the thermostating step at the temperature of 30°C under magnetic stirring. The internal pressure decreases from 3.6 atm to 2.7 atm during the reaction (about 8 hours).
- [0193] After distillation of the unreacted monomers and polymer stripping under vacuum at 150°C for 3 hours 652 mg of polymer are separated.
- 55 [0194] By the ^{19}F -NMR analysis carried out on the polymer dissolved in C_6F_6 it results that the total molar percentage of the MOVE 2 + MOVE 2a perfluorovinylethers in the polymer is 37%; the MOVE 2/MOVE 2a molar ratio in the polymer is 83/17 and it is equal to that of the starting fed mixture.
- [0195] The presence of unreacted monomers is not evident.

[0196] The IR analysis does not show, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds.

[0197] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The T_g determined by DSC, is -44.5°C .

[0198] The TGA shows a weight loss of 10% at 451°C .

[0199] The polymer intrinsic viscosity measured at 30°C in

[0200] Fluorinert® FC-75, is 16.7 ml/g.

EXAMPLE 14

Amorphous copolymer between perfluoro-1,2-dihydro-3,5,8-tri-oxa-1-nonene (H-MOVE 2) and perfluoro-1,2-dihydro-3,5,7-tri-oxa-6-methyl-1-octene (H-MOVE 2a) with molar ratio 88/12.

[0201] In a reactor identical to that described in Example 7, 200 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{-CF}_2\text{Cl}$ and 3.1 g of a H-MOVE 2/H-MOVE 2a 88/12 mixture are introduced.

[0202] The procedure described in Example 7 is followed.

[0203] The recovered reaction raw material appears as a slightly viscous, transparent, colourless and homogeneous solution.

[0204] After distillation of the unreacted monomer and subsequent stripping under vacuum at 150°C for 3 hours, 120 mg of polymer are separated.

[0205] The IR analysis of the obtained polymer shows that, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds are absent.

[0206] The ^{19}F -NMR analysis is in accordance with the copolymer structure having a content of monomers H-MOVE 2 and H-MOVE 2a equal to the H-MOVE 2 and H-MOVE 2a percentages in the reacting mixture. The analysis does not show the presence of unreacted monomers.

[0207] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The polymer T_g determined by DSC, is -58.0°C . The thermogravimetric analysis (TGA) shows a weight loss of 10% at 307°C .

EXAMPLE 15

Terpolymer H-MOVE 2/H-MOVE 2a/TFE.

[0208] In a reactor similar to that described in Example 9, 100 μl of perfluoropropionylperoxide at 6% by weight in $\text{CFCl}_2\text{-CF}_2\text{Cl}$ and 5 mmoles of a H-MOVE 2 (88%) and H-MOVE 2a (12%) mixture and 18 mmoles of tetrafluoroethylene, are introduced.

[0209] The same procedure described in Example 9 is followed.

[0210] At the end of the degassing, the reactor is thermostated at the temperature of 30°C under magnetic stirring. The internal pressure decreases from 6.8 atm to 6.5 atm in about 6 hours (reaction time).

[0211] After distillation of the unreacted monomers, and polymer stripping under vacuum at 150°C for 3 hours, 300 mg of the polymer are separated.

[0212] By ^{19}F -NMR analysis of the polymer dissolved under heating in C_6F_6 it is calculated that the molar percentage of the perfluorovinylethers (H-MOVE 2 + H-MOVE 2a) contained in the polymer is 33%. The H-MOVE 2/H-MOVE 2a molar ratio in the polymer is equal to the H-MOVE 2/H-MOVE 2a molar ratio of the fed mixture. Unreacted monomers are not evident.

[0213] The IR analysis does not show, in the polymer spectrum, absorption bands in the zone of the fluorinated double bonds.

[0214] The DSC graph does not show any melting endothermic curve wherefore the polymer is amorphous. The T_g determined by DSC, is -44.5°C .

[0215] The TGA shows a weight loss of 10% at 450°C .

EXAMPLE 1 (comparative)

Copolymer PVE/TFE.

[0216] In a polymerization reactor identical to that described in Example 9, 250 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{-CF}_2\text{Cl}$, 9.8 mmoles of PVE and 18 mmoles of tetrafluoroethylene, are in sequence introduced.

[0217] The procedure already described in the previous Example 9 is followed until thermostating at the temperature of 30°C under magnetic stirring. The reaction time is of eight hours.

[0218] After distillation of the unreacted monomers and stripping under vacuum at 150°C for 3 hours, 540 mg of polymer are recovered.

[0219] By the ^{19}F -NMR analysis carried out on the polymer dissolved in C_6F_6 it is calculated that the PVE molar percentage in the polymer is 23%.

[0220] The IR analysis shows that, in the polymer spectrum, there are absorption bands in the carboxyl zone, whose intensity is 10 times higher than that obtained from a MOVE 1/TFE copolymer film prepared according to Example 9, and having the same thickness.

[0221] The DSC graph does not show any melting endothermic curve, wherefore the polymer is amorphous. The TGA shows a weight loss of 2% at 427°C and of 10% at 463°C. The T_g , determined by DSC, is + 15°C.

[0222] The polymer intrinsic viscosity, measured at 30°C in Fluorinert® FC-75, is 51 ml/g.

EXAMPLE 2 (comparative)

Copolymer between β -PDE ($\text{CF}_3\text{OCF}_2\text{CF}_2\text{OCF}=\text{CF}_2$)/TFE.

[0223] In a polymerization reactor identical to that described in Example 9, 250 μl of perfluoropropionylperoxide at 3% by weight in $\text{CFCl}_2\text{-CF}_2\text{Cl}$, 10 mmoles of β -PDE and 18 mmoles of tetrafluoroethylene, are in sequence introduced.

[0224] The procedure described in the previous Example 9 is followed until the thermostating step at the temperature of 30°C under magnetic stirring.

[0225] By the ^{19}F -NMR analysis carried out on the polymer purified from the monomers by the processes described in the previous Examples, it is calculated that the molar percentage of β -PDE in the polymer is 23%.

[0226] The DSC graph does not show any melting endothermic curve wherefore the polymer is amorphous. The T_g , determined by DSC, is -4.8°C. This T_g value is clearly higher than those obtainable with the vinyl ethers of the invention (see above).

Claims

1. Fluoroelastomers comprising in the polymer chain units deriving from fluorovinylethers of formula:



wherein R is a $\text{C}_2\text{-C}_6$ linear, branched or $\text{C}_5\text{-C}_6$ cyclic (per) fluoroalkyl group, or a $\text{C}_2\text{-C}_6$ linear, branched (per) fluoro oxyalkyl group containing from one to three oxygen atoms; when R is a fluoroalkyl or fluoroxyalkyl group as above defined it can contain from 1 to 2 atoms, equal to or different from each other, selected from the following: H, Cl, Br, I; X = F, H.

2. Fluoroelastomers according to claim 1, comprising in the polymer chain units deriving from fluorovinylethers of formula:



wherein Y = F, OCF_3 ; X as above defined.

3. Fluoroelastomers according to claims 1 and 2, comprising in the polymer chain units deriving from fluorovinylethers of formula:




wherein Y is as above defined.

4. Fluoroelastomers according to claims 1-3, comprising in the polymer chain units deriving from fluorovinylethers of formula:



(IV)


- 5 5. Fluoroelastomers according to claims 1-4, obtainable by polymerizing the fluorovinylethers mentioned in claims 1-4 with comonomers, using an amount of fluorovinylethers such as to lead to the disappearance of the crystalline domains.
- 10 6. Fluoroelastomers according to claim 5, wherein the amount of fluorovinylethers is higher than 10% by moles, preferably in the range 15-20% by moles, or higher.
- 15 7. Fluoroelastomers according to claims 1-6, wherein the comonomers are fluorinated compounds having at least one polymerizable double bond C=C, optionally containing in the molecule hydrogen and/or chlorine and/or bromine and/or iodine and/or oxygen, said comonomers being able to produce (co)polymers in the presence of radical initiators.
- 20 8. Fluoroelastomers according to claim 7, wherein optional copolymerizable comonomers are non fluorinated C₂-C₈ olefins, preferably ethylene, propylene, isobutylene.
- 25 9. Fluoroelastomers according to claims 7-8, wherein the comonomers are selected from one or more of the following:
- C₂-C₈ perfluoroolefins, preferably tetrafluoroethylene (TFE), hexafluoropropene (HFP), hexafluoroisobutene;
 - C₂-C₈ hydrogenated fluoroolefins, preferably vinyl fluoride (VF), vinylidene fluoride (VDF), trifluoroethylene, CH₂=CH-R²_i perfluoroalkylethylenes, wherein R²_i is a C₁-C₆ perfluoroalkyl;
 - C₂-C₈ chloro- and/or bromo- and/or iodo-fluoroolefins, preferably chlorotrifluoroethylene (CTFE) and bromotrifluoroethylene;
 - CF₂=CFOR²_i (per)fluoroalkylvinylethers (PAVE), wherein R²_i is a C₁-C₆ (per)fluoroalkyl, preferably trifluoromethyl, bromodifluoromethyl or heptafluoropropyl;
 - CF₂=CFOX^a (per)fluoro-oxyalkylvinylethers, wherein X^a is a C₁-C₁₂ alkyl, or a C₁-C₁₂ oxyalkyl, or a C₁-C₁₂ (per) fluoroalkoxyalkyl having one or more ether groups, preferably perfluoro-2-propoxy-propyl;
 - sulphonic monomers having the structure CF₂=CFOX^bSO₂F, wherein X^b = CF₂CF₂, CF₂CF₂CF₂, CF₂CF(CF₂X^c) wherein X^c = F, Cl, Br.
 - a bis-olefin having the general formula



wherein

- 40 R¹₁, R¹₂, R¹₃, R¹₄, R¹₅, R¹₆ equal to or different from each other, are H or C₁-C₅ alkyls;
Z is a C₁-C₁₈ linear or branched alkylene or cycloalkylene radical, optionally containing oxygen atoms, preferably at least partially fluorinated, or a (per)fluoropolyoxyalkylene radical.

- 45 10. Fluoroelastomers according to claim 9, wherein in the bis-olefin of formula (IA), Z is a C₄-C₁₂ perfluoroalkylene radical and R¹₁, R¹₂, R¹₃, R¹₄, R¹₅, R¹₆ are hydrogen.
- 50 11. Fluoroelastomers according to claims 9-10, wherein in the bis-olefin of formula (IA) Z is a (per)fluoropolyoxyalkylene radical, having the formula:



wherein:

- 55 Q is a C₁-C₁₀ alkylene or oxyalkylene radical;
p is 0 or 1;
ma and na are integers such that the ma/na ratio is comprised between 0.2 and 5 and the molecular weight of said (per)fluoropolyoxyalkylene radical is in the range from 500 to 10,000, preferably from 1,000 to 4,000.

12. Fluoroelastomers according to claims 9-11, wherein in the bis-olefin of formula (IA) Q is selected from the following groups:



with $s = 1-3$.

13. Fluoroelastomers according to claims 9-12, wherein the amount in the chain of units deriving from the bis-olefin of formula (IA) is in the range 0.01-1.0 by moles.

14. Fluoroelastomers according to claims 1-13, wherein the base fluoroelastomer structure is selected from:

(1) copolymers based on VDF copolymerized with at least one comonomer selected from $\text{C}_2\text{-C}_8$ perfluoroolefins preferably tetrafluoroethylene (TFE), hexafluoropropene (HFP); $\text{C}_2\text{-C}_8$ chloro- and/or bromo- and/or iodo-fluoroolefins, preferably chlorotrifluoroethylene (CTFE) and bromotrifluoroethylene; $\text{CF}_2=\text{CFOR}_1^1$ (per)fluoroalkylvinylethers (PAVE), wherein R_1^1 is a $\text{C}_1\text{-C}_6$ (per)fluoroalkyl, preferably trifluoromethyl, bromodifluoromethyl, pentafluoropropyl; $\text{CF}_2=\text{CFOX}^t$ perfluoro-oxyalkylvinylethers, wherein X^t is a $\text{C}_1\text{-C}_{12}$ perfluoro-oxyalkyl having one or more ether groups, preferably perfluoro-2-propoxy-propyl; $\text{C}_2\text{-C}_8$ non fluorinated olefins (OI), preferably ethylene and propylene;

(2) copolymers based on TFE copolymerized with at least one comonomer selected from: $\text{CF}_2=\text{CFOR}_1^1$ (per) fluoroalkyl-vinylethers (PAVE), wherein R_1^1 is as above defined; $\text{CF}_2=\text{CFOX}^t$ perfluoro-oxyalkylvinylethers, wherein X^t is as above defined; $\text{C}_2\text{-C}_8$ fluoroolefins containing hydrogen and/or chlorine and/or bromine and/or iodine atoms; $\text{C}_2\text{-C}_8$ non fluorinated olefins (OI).

15. Fluoroelastomers according to claim 14, having the following base monomeric compositions (by moles):

VDF	45-85
HFP and/or PAVE	0-45
TFE	0-30
MOVE	1-45, preferably 5-40
OI	0-40

the sum of HFP+PAVE+MOVE being at most 45%

TFE	50-85
PAVE	0-50
MOVE	1-50, preferably 5-40
OI	0-40

the sum of PAVE+MOVE being at most 50.

16. Fluoroelastomers according to claims 14-15, curable by peroxidic route, optionally in the presence of small amounts of a bis-olefin as above indicated, said fluoroelastomers preferably containing reactive sites, i.e. iodine and/or bromine in the chain, preferably iodine, and/or using an iodinated and/or brominated transfer agent.

17. Fluoroelastomers according to claims 13-15, curable by ionic route, having the following compositions (expressed by moles):

when the fluoroelastomer is used for the preparation of O-rings:

VDF	48-65
HFP	20-35
PAVE	0-6
TFE	0-20

EP 1 148 072 A2

(continued)

MOVE	3- 9
------	------

5 the sum PAVE + MOVE lower than or equal to 10% by moles;
when the fluoroelastomer is used for preparing shaft seals or fuel hoses:

10

VDF	30-47
HFP	20-40
PAVE	0-17
TFE	10-30
MOVE	3-20

15 the sum PAVE+MOVE lower than or equal to 20% by moles.

20

25

30


35

40

45

50

55



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 148 072 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
07.08.2002 Bulletin 2002/32

(51) Int Cl.7: **C08F 216/14, C08F 214/00,
C08F 214/26**

(43) Date of publication A2:
24.10.2001 Bulletin 2001/43

(21) Application number: **01108598.2**

(22) Date of filing: **05.04.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Navarrini, Walter**
Boffalora Ticino, Milano (IT)

(74) Representative: **Sama, Daniele, Dr. et al**
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(30) Priority: **21.04.2000 IT MI000901**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(54) Fluoroelastomers

(57) Fluoroelastomers comprising in the polymer chain units deriving from fluorovinylethers having the formula:



(per) fluoroalkyl group, or a C₂-C₆ linear, branched (per) fluoro oxyalkyl group containing from one to three oxygen atoms; when R is fluoroalkyl or fluoroxyalkyl group as above defined, it can contain from 1 to 2 atoms, equal or different, selected from the following: H, Cl, Br, I; X = F, H.

wherein R is a C₂-C₆ linear, branched or C₅-C₆ cyclic

EP 1 148 072 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 10 8598

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 99 48939 A (DYNEON LLC) 30 September 1999 (1999-09-30) * page 5, line 8; claims * -----	1-17	C08F216/14 C08F214/00 C08F214/26
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08F
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 13 June 2002	Examiner Iraegui Retolaza, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.02 (P04001)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 01 10 8598

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-06-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9948939 A	30-09-1999	BR 9908975 A	05-12-2000
		CA 2324954 A1	30-09-1999
		CN 1294601 T	09-05-2001
		EP 1068248 A1	17-01-2001
		JP 2002507640 T	12-03-2002
		WO 9948939 A1	30-09-1999

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

